

MICRONIC C 30

Calcium Carbonate Natural Micronized

Physical Characteristics

Mineral density	2,7 g/cm ³
Refractive Index	1,59
Hardness (Mohs)	3

Product Description

Equipment - Method

Abrasiveness	70 - 85 g/m ²	Abrasions Tester AT 1000
Brightness L	≥ 96	Minolta Spectrophotometer CM-25CG according to Norm T534 pm 92
b*	≤ 3	
Residue on #325	< 0,5 %	*
Particles d < 2 um	30 - 33%	Size Particles Analyzer Sedigraph III
Medium Diameter (d50%)	≤ 4 μm	
Top Cut (d98%)	≤ 20 μm	

Combined Report


Report by Size Table

Low Diameter (μm)	Cumulative Mass Finer (Percent)	Out of Spec (-%<, +%>)	Difference From Reference (% Finer)	Cum. Mass Standard Deviation (1 tests)
2.000	30.1	11.8	14.4	0.0

Report by Mass Percent

Low Diameter (μm)	Cumulative Mass Finer (Percent)	Out of Spec (-%<, +%>)	Difference From Reference (% Finer)	Cum. Mass Standard Deviation (1 tests)
17.32	98.0	0.0	6.2	0.0
3.482	50.0	2.7	5.5	0.0

Cumulative Finer Mass Percent vs. Diameter



Presentation

Fine powder provided in big bags of 1000kg or in bags of 25kg.

Storage Conditions

It must be storage under a roof, in minimum humidity conditions and stowed on pallets.

Elaborated: Macarena Vera
 Responsible Of Quality Control
 Date: 28/05/2020

Revision: Ing. Carlos Rizzi
 Quality Manager
 Date: 29/05/2020

Approved: Ing. Julio Corengia
 Industrial Manager
 Date: 01/06/2020